

## Spruce (Nordic), Grade A



### Knots

- Black pin knots up to 5 mm, if not grouped
- Sound, ingrown knots up to 10 % of the width + 35 mm permitted
- Partially ingrown, black edged and unsound knots (not fallen): 10 % of the width + 10 mm
- Knocked-out areas in knots: up to 20 % of knot surface

### Cracks

- End cracks not longer than twice the board width permitted  
For solid wood flooring, scattered, not longer than half of the width
- Hairline cracks (hardly visible) permitted

### Resin pockets

- Scattered up to 2 mm x 25 mm permitted, except for one pocket up to 5 mm x 50 mm, each 1.5 m long

### Natural colour variation

- Board face – no discolourations permitted (discolourations on back permitted)
- Bark pockets permitted: scattered up to 5 mm x 50 mm

### Pest attack

- Inadmissible

*Production and sorting implemented according to factory standards based on EN 13629 (solid hardwood boards). Occasional deviations in grade cannot be completely ruled out. Provided that this amount is less than 5 per cent of the ordered quantity, there are no grounds for claim. Wood is a natural product and is characterized by variations in colour and structure.*